

Product	Delivery Form		Composition				Specification	
	Solid %±1	Solvent Composition	Type of Oil	Oil%	PA%	Type of Polyol	Acid Value	Viscosity Gardner @25 °C
LA-ARAB (SW61-20/55)	70	White Spirit	Sunflower or Soya bean	61	28	Penta	8 Max.	Z8 at 70% & Y-Z at 55%
LA-ARAB (SW60-36/55)	70	White Spirit	Sunflower or Soya bean	60	29	Penta	8 Max.	Z10 at 70% & Z2 at 55%
LA-ARAB (SW61-9/55)	70	White Spirit	Sunflower or Soya bean	61	28	Penta	12 Max.	Z6 at 70% & V-W at 55%
LA-ARAB (SW64-65/70)	70	White Spirit	Sunflower or Soya bean	64	25	Mixed Polyol	10 Max.	Approx. Z4 at 70%
LA-ARAB (SW62-15/55)	70	White Spirit	Non yellowing Sunflower fatty acids	62	28	Mixed Polyol	12 Max.	Z8 at 70% & Y-Z at 55%
LA-ARAB (SFW61-97/70)	70	White Spirit	Sunflower oil	61	25	Penta	8 Max.	Z5-Z6 at 70%
LA-ARAB (SFFW63-40/70)	70	White Spirit	Linseed	63	26	Penta	12 Max.	Z2-Z3 at 70%
LA-ARAB (SW55-30/55)	70	White Spirit	Sunflower or Soya bean	55	29	Penta	10 Max.	Z1-Z2 at 55%
LA-ARAB (SW65-4/60)	75	White Spirit	Sunflower or Soya bean	65	24	Penta	10 Max.	O-P at 60% & Y-Z at 70%
LA-ARAB (SWZ68-50/75)	85	Zero aromatic W. Spirit (D40)	Sunflower or Soya bean	68	23	Penta	10 Max.	Z3-Z4 at 75%
LA-ARAB (SWZ64-5/70)	80	Zero aromatic W. Spirit (D40)	Sunflower or Soya bean	64	24	Penta	10 Max.	O-T at 70%
LA-ARAB (S68-15/100)	99	--	Linseed	68	20	Penta	12 Max.	W-Y at 100%
LA-ARAB (LRW60-19/55)	70	White Spirit	Linoleic rich fatty acid	60	29	Mixed Polyol	12 Max.	Z8 at 70% & Y-Z at 55%
LA-ARAB (S85-27/100)	99	--	Sunflower or Soya bean	85	8	Mixed Polyol	15 Max.	Z1-Z3 at 100%
LA-ARAB (SFW 61-20/55)	70	White Spirit	Non yellowing Sunflower fatty acids	61	28	Penta	8 Max.	Y-Z@55%

		Performance	Suggested Uses
Viscosity C Poise @25 °C	Color Gardner		
2000 at 55%	5 Max.	Good gloss & gloss retention, Good adhesion, Brush ability & leveling, good yellowing resistance & hardness.	Interior & exterior house paints, Varnish floor sealers, Porch & deck enamels.
3600 at 55%	5 Max.	Very high Viscosity, Good Adhesion & hardness, Light color, High gloss & gloss retention.	Interior & exterior house paints, Gloss enamel, high viscosity paints, Varnish & floor sealers.
900 at 55%	5 Max.	High gloss & gloss retention, Brush ability & leveling, very good flexibility.	Interior & exterior house paints, non yellowing medium viscosity paints, Gloss paints, Varnish & floor sealers (with light color).
6500 at 70%	5 Max.	Brush ability & leveling, Light color with good yellowing resistance properties, High gloss & gloss retention.	High gloss paints, Exterior house paints.
1500 at 55%	5 Max.	Very good gloss & gloss retention, Good exterior durability, Very good color retention.	Highly recommended for white/light colored high gloss paints because of its interior non yellowing properties in dark, Gloss enamel for outdoor.
9700 at 70%	5 Max.	Excellent yellowing resistance in dark, Very good outdoor durability, Light color, High gloss & gloss retention.	Interior non yellowing paints, Exterior high gloss paints, Very special for white enamels.
4000 at 70%	5 Max.	Excellent yellowing resistance in the dark, Brush ability & leveling, Light color with good color retention, High gloss & gloss retention.	Interior & exterior house paints, Varnish floor sealers.
3000 at 55%	5 Max.	Chain stopped, Fast drying, Good gloss & gloss retention, Very good yellowing resistance & hardness.	Interior & exterior house paints, Very low viscosity paints, High build Varnish & floor sealers.
400 at 60%	5 Max.	Very low Viscosity, Good Adhesion & hardness, Light color, High gloss & gloss retention, Brush ability & leveling.	Very high gloss enamels, Interior & exterior decorative paints, Special for low VOC paints.
5000 at 75%	5 Max.	High solid alkyd resin, High gloss & gloss retention, Medium Viscosity, High solid alkyd resin, very good pigment wetting properties.	Very high gloss enamels, Interior & exterior decorative paints, Special for low VOC paints., Diluted with k. odorless.
500 at 70%	6 Max.	High solid alkyd resin, High gloss & gloss retention, Very Low Viscosity, Very good pigment wetting properties.	Interior & exterior decorative paints, Varnish, Very low viscosity paints & High gloss finishes.
1500 at 100%	6 Max.	Ultra high solid content, Very low viscosity, High gloss, Very good leveling & Very good Brushability.	Interior and exterior house paints, colored high gloss enamel, high viscosity paints, varnish and oor sealers.
1900 at 55%	5 Max.	Good adhesion and medium hardness, high gloss and gloss retention.	Interior & exterior house paints, Colored high gloss enamel, High viscosity paints, Varnish & floor sealers.
2700 at 100%	6 Max.	Ultra high solid, very good gloss and levelling properties.	Interior and exterior decorative paint.
2000 at 55%	5 Max.	Excellent yellowing resistance, High gloss and gloss retention.	Highly recommended for white colored high gloss paints.